

# Technical Specifications for Vacuum Wet Pressed Kerbstones in Half Batter (HB) Profile

### **Product Description**

Supply of Half Batter Profile Kerbstones of VYARA make, as per the below profile drawing, manufactured on Vacuum Wet Press Machine with hydraulic pressing of wet concrete mixture to a minimum of 400 tons with simultaneous vacuuming, using ECO filters with pimple finish. Brand name of the vendor should be embossed on the back side of every piece.

| Profile- Half Batter (HB)  | Length<br>(mm) | Height<br>(mm) | Thickness<br>(mm) |
|--|----------------|----------------|-------------------|
| A county mass  | 1000           | 300            | 100               |
| 10 mental sections of the section of the sect | 600            | 450            | 150/125/100       |
| 175mm 165mm 3-7  | 600            | 375            | 150/125/100       |



| Profile- Half Batter (HB) | Length<br>(mm) | Height<br>(mm) | Thickness<br>(mm)     |
|---------------------------|----------------|----------------|-----------------------|
| 155mm                     | 600            | 300            | 150/125/100/<br>80/65 |
| 108mm 14.mm               | 600            | 215            | 150/125               |
| 150mm 144 mm              | 600            | 175            | 150/125               |
| 10 maggi                  | 300            | 600            | 150/125               |
| 100mm 14 mm moor          | 500            | 325            | 165/150/125           |



#### **Technical Parameters**

| Sr. | Parameters  | Minimum Requirements  |                       |  |
|-----|---|---|-----------------------|--|
| 1.  | Tolerance in Size   | ±1.5 mm   |                       |  |
|     | (Length & Height)   |   |                       |  |
| 2.  | Tolerance in Thickness  | ±4 mm   |                       |  |
| 3.  | Water Absorption  | Average not over 6%   |                       |  |
| 4.  | Permissible Deviations of   | Length of gauge   | Permissible deviation |  |
|     | Flatness and Straightness (for faces described as flat and edges described as straight) | 300 mm  | ±1.5 mm               |  |
|     |   | 400 mm  | ±2.0 mm               |  |
|     |   | 500 mm  | ±2.5 mm               |  |
|     |   | 800 mm  | ±4.0 mm               |  |
| 5.  | Average Bending Characteristic  | 4.5 MPa   |                       |  |
| 6.  | Minimum Bending Strength  | 4.0 MPa   |                       |  |
| 7.  | Visual  | The face of the kerbstone shall not exhibit defects such as cracking or flaking |                       |  |
|     |   |   |                       |  |

### **Manufacturing & Quality Assurance**

# Manufacturing Process:

The kerbstone must be manufactured on Vacuum Wet Press Machine with hydraulic pressing of wet concrete mixture to a minimum of 400 tons with simultaneous vacuuming, using ECO filters with pimple finish and with vendor brand name embossed on backside of each kerbstone.

### **Quality Certifications:**

- The manufacturer must be ISO 9001:2015 certified or have equivalent quality management systems in place to ensure quality product.
- Test reports should be accompanied along with the materials as required by EIC

# **Sustainability Requirements:**

The product must meet the sustainability criteria and should be certified as a green product (GreenPro) by CII.

# **Testing Facilities:**

The manufacturer must have an in-house laboratory equipped to perform these tests: Water Absorption | Bending Strength | Dimensional Accuracy

Vyara Tiles Limited

903-904 Rajhans Montessa, Near Le Meridian, Dumas Road, Surat 395007

Ph: 0261-2471595, 2472444 | E-mail: info@vyaratiles.in | Website: www.vyaratiles.in