



Specifications for Vacuum Wet Pressed Transition Kerbstones from Half Batter (HB) to Splay (SP) profile

Supply of EN type **Transition Kerbs (from Half Batter to Splay profile) in left hand or right hand orientation** of VYARA make as per the below profile drawing, manufactured on Vacuum Wet Press Machine with hydraulic pressing of wet concrete mixture to a minimum of 400 tons with simultaneous vacuuming, using ECO filters with pimple finish

| Profile- Transition HB to SP (Left Hand) | Profile- Transition HB to SP (Right Hand) | Length (mm) | Width (mm) | Thickness (mm) |
|--|--|----------------|---------------|----------------|
| 1 Sonten | 150mm 150mm | 600 | 300 | 150 |
| 125mm | 2500mm 100mm + 100mm + 100mm + 100mm | 600 | 300 | 125 |
| 100 ₀₀₀ | Septiment to the septiment of the septim | 600 | 300 | 100 |

| Sr. | Parameters | Minimum Requirements |
|-----|--------------------------------------|----------------------|
| 1. | Percentage Water Absorption | Not over 6% |
| 2. | Tolerance in size (length + breadth) | ±1.5mm |
| 3. | Tolerance in Thickness of block | ± 4mm |



- The face of the kerb shall not exhibit defects such as cracking or flaking when examined.
- For faces described as flat and edges described as straight, the permissible deviations on flatness and straightness are given in Table 1

Table 1- Permissible deviations of flatness and straightness

| Length of gauge | Permissible deviation of flatness and straightness |
|-----------------|--|
| mm | Mm |
| 300 | ±1.5 |
| 400 | ±2.0 |
| 500 | ±2.5 |
| 800 | ±4.0 |

Bending Characteristic of Kerb as per Table 2

Table 2- Bending Characteristic

| Characteristic bending strength MPa | Minimum bending strength Mpa |
|-------------------------------------|---------------------------------|
| 4.5 | 4.0 |

- The manufacturing company must be an ISO 9001 certified Company or should have equivalent quality management systems in place to ensure quality product.
- The Kerbstone must meet the sustainability criteria and should be certified as a green product by CII.
- The Kerbstone material must be tested at the manufacturer's laboratory before dispatch for: Bending strength, Water absorption, and dimensional accuracy. Internal test report needed with every supply.

Testing to be carried out in accordance with EN 1340