

Specifications for Cement Concrete Wet Cast Bellezza Tiles (300x300x30mm)

Supply of Reflective Type (Wet Cast) finish Chequered Tiles with

- wear resistant aggregates colour coordinated aggregates in face mix.
- Colours specified by the architects, using UV resistant colour pigments from Lanxess.
- supplied with two coats of UV resistant acrylic lacquer coating

Sr.	Parameters	Minimum Requirements (Testing as per IS 13801:1993)
1.	Percentage Water Absorption	Not over 6%
2.	Wet transverse strength	Not less than 4N/mm ²
3.	Average wear in Thickness- Abrasion	Average wear not more than 2mm
4.	Tolerance in Size (length + breadth)	± 1.5mm
5.	Thickness of wearing layer	Not less than 8mm
6.	Variation in Thickness of tiles	± 3mm
7.	Flatness of tile surface	Concavity / convexity not to exceed 1mm
8.	Colours	UV Light resistant fast colours from Lanxess only to be used

- The Chequered Tiles must confirm to IS 13801: 1993.
- The Tiles must be manufactured on automatic machines with mechanical vibration and rubberized moulds.
- The manufacturing company must be an ISO 9001:2015 certified Company or should have equivalent quality management systems in place to ensure quality product.
- The tiles must meet the sustainability criteria and should be certified as a green product by CII.
- The Tiles will be made using wear resistant materials in the face mix as specified by the architects.
- The Tiles must be cured in a controlled environment to ensure efflorescence free material.
- The manufacturer must have in house testing laboratory to carry out all testing including Compressive strength testing, Water absorption, abrasion resistance etc.